



Pharmaceutical Nanotechnology

Paclitaxel Encapsulated in Halloysite Clay Nanotubes for Intestinal and Intracellular Delivery



Raghuvara Yendluri¹, Yuri Lvov^{1,2,*}, Melgardt M. de Villiers³, Vladimir Vinokurov², Ekaterina Naumenko⁴, Evgenya Tarasova⁴, Rawil Fakhrullin^{1,4,*}

¹ Institute for Micromanufacturing, Louisiana Tech University, Ruston, Louisiana 71272

² I. Gubkin Russian State University of Oil and Gas, Moscow 119991, Russia

³ School of Pharmacy, University of Wisconsin-Madison, Madison, Wisconsin 53705

⁴ Bionanotechnology Lab, Institute of Fundamental Medicine and Biology, Kazan Federal University, Kazan, Republic of Tatarstan 420008, Russia

ARTICLE INFO

Article history:

Received 12 April 2017

Revised 16 May 2017

Accepted 22 May 2017

Available online 7 June 2017

Keywords:

halloysite

clay nanotubes

paclitaxel

tablets

pH-sensitive drug release

intracellular delivery drug release

intracellular delivery

ABSTRACT

Naturally formed halloysite tubules have a length of 1 μm and lumens with a diameter of 12–15 nm which can be loaded with drugs. Halloysite's biocompatibility allows for its safe delivering to cells at a concentration of up to 0.5 mg/mL. We encapsulated the anticancer drug paclitaxel in halloysite and evaluated the drug release kinetics in simulated gastric and intestinal conditions. To facilitate maximum drug release in intestinal tract, halloysite tubes were coated with the pH-responsive polymer poly(methacrylic acid-co-methyl methacrylate). Release kinetics indicated a triggered drug release pattern at higher pH, corresponding to digestive tract environment. Tablets containing halloysite, loaded with paclitaxel, as a compression excipient were formulated with drug release occurring at a sustained rate. *In vitro* anti-cancer effects of paclitaxel-loaded halloysite nanotubes were evaluated on human cancer cells. In all the treated cell samples, polyploid nuclei of different sizes and fragmented chromatin were observed, indicating a high therapeutic effect of halloysite formulated paclitaxel.

© 2017 American Pharmacists Association®. Published by Elsevier Inc. All rights reserved.

Introduction

Halloysite clay is a natural, abundantly available tubular material formed by rolled kaolin sheets and its chemical formula is $\text{Al}_2\text{Si}_2\text{O}_5(\text{OH})_4$. The diameter of halloysite tubes is 50–70 nm with an inner lumen of 12–15 nm and length of 500–1000 nm (Fig. 1). The tube wall contains approximately 15 closely packed aluminosilicate sheets with a spacing of approximately 0.72 nm and has a density of 2.53 g/cm³. The surface charge polarity of halloysite tubes is negative and its inner lumen is positively charged due to the presence of silica and alumina on the outside and inside, respectively. Halloysite is a safe, biocompatible nanomaterial.^{1–4} All these properties advocated the use of halloysite nanotubes (HNT) as natural nanocontainers for loading and sustained release of proteins, DNA, and drugs.^{5–10}

Halloysite was utilized for the loading of tetracycline, kellin, ofloxacin, gentamicin, aspirin, dexamethasone, nifedipine, curcumin, doxorubicin, and acetaminophen at 10–15 wt.% from aqueous/nonaqueous polar solvents.^{6–15} The prepared composites remained stable over extended periods in dry conditions and then released the captured drugs in aqueous or serum/blood for 5–10 h. Bio-macromolecules, such as enzymes immobilized on halloysite surface and in lumen, enhanced stability at extreme environmental conditions of pH and temperature.¹⁶ Owing to halloysite's different charge polarity on the outside and inside, dual enzyme composites were prepared in media of different pH, depending on the isoelectric point of enzyme. Halloysite was also utilized to impart mechanical strength to polymer-based scaffolds for tissue engineering applications.¹⁷

Halloysite is a safe, biocompatible material, allowing for efficient removal from an organism with macrophages. It was shown for many biological cells and tissues that halloysite is safe at concentrations of up to 0.5 mg/mL, an exceptionally high safe concentration for inorganic inclusions into cells.^{3,4} Apart from cell toxicity studies, HNTs were used as an oral feed for chickens and piglets to remove toxins.¹⁸ Halloysite was suggested as a novel tablet compression excipient for oral drug delivery and was used in the

* Correspondence to: Yuri Lvov (Telephone: 318-257-5144; Fax: 318-257-5104) and Rawil Fakhrullin (Telephone: +7(843) 590-55-06; Fax: +7(843) 233-78-14).

E-mail addresses: ylvov@latech.edu (Y. Lvov), kazanbio@gmail.com (R. Fakhrullin).